

Use Information: This paragraph is informational only and is not exclusively definitive of the end use.

For high quality multicolor face and back offset printing of covers for book, periodicals, etc. Printed matter may include text, line illustrations, halftones up to 150-line screen. and solid reverses.

Stock: Ground wood pulp, not to exceed 1%.

Note: Not less than 10% postconsumer fiber. Any percent over 10 percentage points, is encouraged, provided that the requirements of this Standard are met.

Basis weight: 20 by 26 inches, 500

sheets (pounds)	60/65	80	100
A tolerance of $\pm 5\%$ shall be allowed.			

Bursting strength: Average not

less than (lb/in ²)	40	50	60
---------------------------------------	----	----	----

Tearing strength: Average each

direction not less than (grams)	80	100	120
---------------------------------------	----	-----	-----

Opacity: Average not less than

(percent)	95	95	96
-----------------	----	----	----

No individual specimen shall

average less than (percent)	93	93	94
-----------------------------------	----	----	----

Gloss (75°): Average each side not to exceed

(percent).....	25
----------------	----

Smoothness of coating: Average each side

not to exceed (Sheffield units)	120
---------------------------------------	-----

General appearance: Paper shall conform to the standard sample(s) established by the Government.

Brightness: Shall not less than target 83% or as specified.

Color: The paper in the order (or publication) shall be uniform and the color variation shall not exceed DE(CIELAB) = 1.0.

Formation: Coating shall be uniform; shall be uniformly applied; shall not be gritty, mottled, stippled, or ribbed in appearance; and shall not exhibit cracks or flake off.

Cleanliness: The dirt count for each side of the paper shall not exceed 100 specks per square meter. No sample sheet (600 to 650 cm² in size) shall contain more than one defect with equivalent area of 0.25 mm² or greater.

OPTION

Alkaline paper. This option is for products requiring above average permanence. Add / replace the following properties.

Stock: 100% bleached chemical woodpulp.

Note: Not less than 10% postconsumer fiber. Any percent over 10 percentage points, is encouraged, provided that the requirements of this Standard are met.

Acidity: pH value by cold extraction. Average, not less than 7.0 for both the coating and base paper.

Note: Any deviation in this requirement is sufficient cause for rejection of the paper.

Testing: Shall be conducted in accordance with methods in part 2, *Government Paper Specification Standards*. The acceptance criteria Part 4 shall apply.